

ALFONIC® TDA-6 Ethoxylate

Technical Data Sheet

SASOL
reaching new frontiers



Description

Sasol North America Inc.'s ALFONIC® TDA-6 Alcohol Ethoxylate is a biodegradable nonionic surfactant derived from Isotridecyl Alcohol. It is then ethoxylated to an average of six moles of ethylene oxide. This ethoxylate is essentially 100% active unless diluted with water.

ALFONIC® TDA-6 Ethoxylate is a clear, colorless liquid. Because it is a low-mole ethoxylate, it is sparingly soluble in water but soluble in hydrocarbons.

Applications

ALFONIC® TDA-6 Ethoxylate can be used in a wide variety of applications. It can be used as a high quality, biodegradable emulsifier and also in industrial and institutional cleaning products. ALFONIC® TDA-6 Ethoxylate can be used in such industrial application as textile and leather processing, plastic additives, pulp and paper processing, metal cleaning, and agricultural adjuvants.

Properties

Typical physical properties are listed in the table to the right. Actual properties will vary from lot to lot.

Contact Information

For technical information or samples:

Sasol North America

Product Steward

2201 Old Spanish Trail

Westlake, Louisiana 70669

Telephone: (337)494-4133

Fax: (281)368-0819

TDS.ProductSteward@us.sasol.com

For sales and pricing information contact a sales representative at:

Sasol North America

900 Threadneedle

Houston, TX 77079-2990

Telephone: (281)588-3000

Fax: (281)368-1531

Email: info@us.sasol.com

Typical Properties	ALFONIC® TDA-6
Average Molecular Wt.	466
Color, APHA	< 50
Hydroxyl Number	122 - 128
Water, Wt %	< 0.1
Glycol, Wt %	< 2.0
Free Alcohol, wt%	<10
Density, g/mL @ 40°C	0.9695
Flash Point °C (°F)	152 (305.6)
Cloud Point °C (°F), BDG	70 (158)
Melting Range, °C (°F)	9-18 (48.2– 64.4)
Boiling Point, °C (°F)	>250 (482)
Viscosity, cSt @ 40°C	19.977
pH, 5% in IPA/Water	6 - 8
Vapor Density, Air = 1	~15
Avg. EO Content, moles	6
Avg. EO Content, Wt. %	56
Free EO, PPM	< 1
Solubility in Water, g/L	Yes
HLB, calculated	11.2

ALFONIC is a registered trademark of Sasol North America Inc.

The preceding data is based on tests and experience, which Sasol North America believes reliable, and is supplied for informational purposes only. Sasol North America expressly disclaims any liability whatsoever for damage or injury which results from the use of the preceding data and nothing contained therein shall constitute a guarantee, warranty, or representation (including freedom from patent liability) by Sasol North America with respect to the data, the product described, or its fitness for use for any specific purpose, even if that purpose is known to Sasol North America.

For detailed safety and handling information regarding these products, please refer to the respective Sasol North America Material Safety Data Sheet.

7/10/12